

#### FIELD OF APPLICATION

Doors and windows, garden furniture, claddings, balconies, enclosures, matchboardings, beams.

#### INFORMATION

This coating is soft to the touch. It makes the wood water-repellent, resistant, durable and enhances its natural matt aspect. This product protects the wood from atmospheric agents. 5-10% dilution with water is possible to improve the application of the product.

#### **INSTRUCTIONS**

Stained/impregnated wood. It is possible to apply RC2030 on wood treated with low-solid content dyes or wood stains. Once the surface has been cleaned, sand with sandpaper or scotch brite. Then remove the powder and apply 1-2 coats of product. Coated wood. On a paint finish in good condition, it is necessary to sand with 320 grit sandpaper. Clean the surface, then proceed to paint. On a paint finish in bad condition, sand with 80-150 grit sandpaper to bring the wood back to the raw condition. Clean the surface and proceed to paint. Application of 1-2 coats of Gel Wood Stain RGxx80 before RC2030 is recommended.

# **MAINTENANCE**

In case of objects, which are very exposed to the atmospheric agents, it is sufficient to treat only the parts that begin to deteriorate. Slightly sand the object with 220-320 grit sandpaper, remove the powder and apply one coat of the desired colour. On the most deteriorated parts it is possible to apply a second coat. If the object is not much exposed to the atmospheric agents, the maintenance operations will be less frequent. To extend the protective action of the film and the aspect of the object it is recommended to clean with Neutral Detergent T.Clean RR1050 and Brightener T.Top+ RR1250 every six months. Avoid aggressive detergents.

### **OVERCOATING**

Waxy Topcoat RC2030.

# **PACKAGING**

0,75 L

2,5 L

5 L

25 L









Storage > 5°C



Painting > 10°C



Ready to use



Brush Spray gun



Yield 10 m<sup>2</sup>/L



Mix it well before use



Tack-free 2 h



Drying time between the coats 4-6 h



Final drying time 12 h



Solid content  $32 \pm 3 \%$ 



Viscosity DIN8 14  $\pm$  3"



Specific weight  $1,05 \pm 0,1 \text{ g/cm}^3$ 



pH 8,5 ± 1,0



Gloss level 12

