



## RP1060 GRAIN FILLER

### FIELD OF APPLICATION

Wood floorings and furniture.

### INFORMATION

It is a transparent primer to be applied on wood floorings and furniture. It is formulated with acrylic-polyurethane resins, it is elastic and can be easily sanded. To improve chemical and mechanical resistances, RP1060 can be catalyzed with 10% XD5200 of Solid range. In this case, wait for the complete drying before applying the following coat.

### INSTRUCTIONS

Sand the raw wood with 150 grit sandpaper and remove the powder with vacuum-cleaner. Apply 1-2 coats of RP1060 at an interval of 2-4 hours. Do not sand between the two coats. Wait for 24 hours before proceeding with the next sanding step, then apply Floorings and furniture topcoat RP1160 or RP2260.

### OVERCOATING

Floorings and furniture topcoats RPxx60.

### PACKAGING

0,75 L

2,5 L



Storage  
> 5°C



Painting  
> 10°C



Ready to use



Brush  
Spray gun  
Roller



Yield  
10 m²/L



Mix it well  
before use



Tack-free  
2 h



Drying time  
between the coats  
4 h



Final drying time  
24 h



Solid content  
33 ± 3 %



Viscosity  
DIN4 17 ± 3"



Specific weight  
1,03 ± 0,1 g/cm³



pH  
8,0 ± 1,0



**RP1060**  
TRANSPARENT